


DT-4100

Graphite tape - corrugated

DAIKOTE
INNOVATIVE SOLUTIONS



Style	Description	Picture	pH	TEMP °C	m/sec	Pressure bar
Style 4100 Tape	Graphite tape - corrugated		0 -14	-200 ~ +450 (Oxidising) -200 ~ +650 (Non-)	20	30 - Rotary (Pumps) 300 - Stationary (Valves)

Description

Style 4100 tape is corrugated Graphite with different widths as required. The rolls are cut to a standard 15m length for ease of use. The corrugation makes the tape more flexible and less prone to tear.

Construction

Style 4100 is made from high quality natural graphite flakes. The Natural graphite flake is chemically treated to form a Graphite Intercalation Compound. This intercalation compound is then rapidly heated to decomposition; the result is a rapid expansion of the particle size. The bulk density of the wormlike graphite powders is about 0.003g/cc. The graphite powders are formed into graphite foil by rolling the powders. No binders are used in the process of making the expanded graphite foil. The foil is then cut to the required width and corrugated for ease of handling.

Application

This product is ideally suited for both pump and valve applications as well as for flange gaskets. Especially useful as die-formed rings, in-situ packing rings and high-pressure bonnet seals in almost every application. This product can substitute the need for braided packing. Forms part of any emission reduction program in valves as well as water reduction programs in pumps.

SPECIFICATION

ITEM	UNIT	MAGNITUDE
Tolerance of density	g/cm ³	≤± 0.05
Tolerance of thickness	mm	≤± 0.03
Carbon content	%	98 ~ 99.9
Tensile strength	Mpa	≤ 3.5
Compressibility	%	> 40
Recovery	%	> 10
Sulphur content	ppm	≤ 1000
Chlorine content	ppm	≤ 50
Ignition Loss: 450°C/1h - 600°C/1h	%	≤ 1.0 - ≤ 20
Volumetric Density	g/cm ³	0.7 ~ 1.2
Working Temperature	°C	-200 ~ +450 (Oxidising)
Pressure	bar	30 Rotary / 300 Stationary
Shaft Speed	m/sec	20
Friction Factor		<0.18